

LISTING OF THE CLAIMS

Claims 1-30 (Canceled)

Claim 31 (Original): A method of manufacturing a power MOSFET, comprising:
epitaxially growing a drift layer of a first conductivity type on a first conductivity type semiconductor substrate used as a drain layer, said drift layer being doped with impurities having a concentration distribution increasing up to said semiconductor substrate;
epitaxially growing a base layer of a second conductivity type on said drift layer;
forming a source region of the first conductivity type on said base layer;
forming a trench penetrating said source region and said base layer to reach at said drift layer; and
forming a trenched gate structure including a gate insulating film and a gate electrode, said gate insulating film having a thin portion facing said base layer and a thick portion facing said drift layer.

Claim 32 (Currently Amended): The method of manufacturing a power MOSFET according to Claim 31, wherein said forming the drift layer comprises:

forming a first epitaxial layer of the first conductivity type on said semiconductor substrate with a first impurity concentration;
forming a second epitaxial layer of the first conductivity type ~~of~~ on said first epitaxial layer with a second impurity concentration lower than ~~that~~ the first impurity concentration of said first epitaxial layer; and
heat treating said first and second epitaxial layers for smoothing the first and second impurity concentrations.

Docket. No.: 251907US-2S DIV
Inventor: Syotaro ONO, et al.

Claim 33 (Original): The method of manufacturing a power MOSFET according to Claim 32, which further comprises:

implanting impurities from a surface of said second epitaxial layer up to a predetermined depth thereof; and

diffusing the implanted impurities into said second epitaxial layer to form a peak of the impurity concentration in said second epitaxial layer.